

## SCALA BRINELL

<b>Essenza</b>	<b>Durezza (Kg/mm<sup>2</sup>)</b>
<b>Bamboo pressato</b>	<b>11.9</b>
<b>Bamboo natura</b>	<b>11.77</b>
Ulivo	6.08
Ipe	5.95
<b>Bamboo classico</b>	<b>4.7</b>
Cabreuva	4.5
Jatoba	4.3
Merbau	4.1

<b>Essenza</b>	<b>Durezza (Kg/mm<sup>2</sup>)</b>
Doussiè Africa	4
Afrormosia	4
Wengè	4
Faggio	3.8
Teak	3.5
Rovere	3.5
Iroko	3.5
Larice	2.6